

DialogWeb

2/9/1 (Item 1 from file: 351)

002513793

WPI ACC No: 1980-31818C/198018

wood surface treatment by priming and applying top coat -
 where undercoat contains alkylenediamine and glycidyl dicarboxylate and
 top coat is polyurethane or alkyd resin

Patent Assignee: MATSUSHITA ELECTRIC WORKS LTD (MATW)

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 55039239	A	19800319				198018 B

Priority Applications (No Type Date): JP 78111928 A 19780911

Abstract (Basic): JP 55039239 A

A surface treatment method for wood comprises (1) applying paint composed primarily of an alkylenediamine and a glycidyl diester of an unsatd. carboxylic acid on the surface of wood in the presence of a radical polymerisation initiator to form undercoat, and then (2) coating a finish paint composed of urethane resin or alkyd resin is coated on the surface of the undercoat.

The surface treatment provides a soft and tough protective film, in which the length of surface cracks which develop with time is remarkably small, thus keeping wood from decaying and deteriorating due to air, water sunlight, etc.

Derwent Class: A82; F09; G02; P42

International Patent Class (Additional): B05D-007/06; C09D-005/00

Derwent WPI (Dialog® File 351): (c) 2001 Derwent Info Ltd. All rights reserved.

2/9/2 (Item 1 from file: 347)

00551639 **Image available**

SURFACE TREATING METHOD FOR WOOD

Pub. No.: 55-039239 [JP 55039239 A]

Published: March 19, 1980 (19800319)

Inventor: ITO TATSUO

NAKANISHI TOSHIO

Applicant: MATSUSHITA ELECTRIC WORKS LTD [000583] (A Japanese Company or Corporation), JP (Japan)

Application No.: 53-111928 [JP 78111928]

Filed: September 11, 1978 (19780911)

International Class: [3] B05D-007/06; C09D-005/00

JAPIO Class: 14.7 (ORGANIC CHEMISTRY -- Coating Material Adhesives)

Journal: Section: C, Section No. 12, Vol. 04, No. 73, Pg. 101, May 28, 1980 (19800528)

ABSTRACT

PURPOSE: To make short the length of generated cracks, by applying to the surface of wood the paint composed of alkylenediamine and glycidyl ester of unsaturated carboxylic acid under coexistence of the radical polymerization initiator, and next, by applying the finishing paint like as urethane resin, etc., to the surface of above undercoat film.

CONSTITUTION: Alkylenediamine (ethylene diamine, for example) and glycidyl ester of unsaturated carboxylic acid shown by the formula (in

JP55039239abs.txt

which, R is $C(\text{sub } n)H(\text{sub } 2n+1)$ and $n=0-3$ at mole ratio 1:0.5-2.5 are dissolved into MEK, etc. After the radical polymerization initiator is added to above prepared paint, this paint is applied to the surface of wood at a rate 1.5-30g/m², and then, the paint film is heated to 40-120 deg.C for less than 15 minutes; hereby, the undercoat film is formed. Next, onto this undercoat film, the finishing paint like as urethane resin, alkyd resin, etc., is applied.

JAPIO (Dialog® File 347): (c) 2001 JPO & JAPIO. All rights reserved.

© 2001 The Dialog Corporation plc